

# PRODUCT DATA



## COLD GALVANISE

### Type

Cold Galvanise Coating for mild-steel surfaces. Also suitable for the touch-up of damaged Galvanised Iron surfaces.

### Appearance

Matt coating containing a modified rubber with Zinc Dust and Zinc Oxide Pigmentation. Also has a greyish appearance.

### Properties

One pack Zinc-rich Primer to protect steelwork under humid, Industrial and Marine environments. Optimum anti-corrosive results are obtained on grit blasted steel.

**Application Method:** Brushing, conventional air spray, airless spray.

**Brushing:** Mineral Turpentine

**Spraying:** Xylene

**Spreading Rate:** ± 15m<sup>2</sup> per litre on smooth surfaces.

**Drying Time:** 1 Hour

**Recoating Time:** 8 Hours

**Cleaning of Utensils:** Xylene

**Standard Film Thickness:** 30 – 40 microns

**Packaging Sizes:** 2kg and 1kg