

# PRODUCT DATA

## MASONRY PRIMER



### Type

Masonry Primer is a Pliolite-based 1<sup>st</sup> Coater for Dry Plastered Surfaces.

### Appearance

Masonry Primer dries to a smooth finish with a low sheen.

### Properties and Uses

Titanium Masonry Primer is a highly alkali resistant, solvent-based coating that allows trapped water vapour to escape through the film. Due to its fine particle size Polymer, it will give better penetration into the substrate than waterbased paints. This product is ideally suited as a sealer for chalky or friable surfaces. Titanium Masonry Primer does not support fungus or mould growth. As Masonry Primer cannot kill fungus, mould or "spoor", the substrate has to be treated with Titanium Anti-Fungus Wash prior to applying the new paint system.

### Surface Preparation

Essential for good paint performance is a sound substrate that has been properly cleaned and prepared. On existing painted surfaces to be redecorated, a small section of paint must be removed to establish the condition of the original paint and the substrate. Where there is doubt, the paint must be removed to a sound base. All surfaces must be dry, free from loose and flaky material, grease and fungus prior to applying the new paint system.

### Application Instructions

These instructions are issued as an aid in determining correct surface preparation, mixing and application procedure and should be closely followed to obtain maximum service from the material.

#### 1. Old Painted One Coat Exterior Plastered Wall Surfaces

- (a) Remove fungus growth, dust, loose and flaky material from the surface by means of a high pressure water jet. Allow the surface to dry properly.
- (b) 1<sup>st</sup> application: Titanium Anti-Fungus Wash. Leave on surface for 24 hours.
- (c) Fill imperfections with Titanium Ti-Fill.
- (d) 1<sup>st</sup> coat: Titanium Masonry Primer thinned with 10% Mineral Turpentine.
- (e) 2<sup>nd</sup> and 3<sup>rd</sup> coat: Titanium Paints Quality Products.

#### 2. New Interior One Coat Plaster or New Interior Two Coat Plaster (Crestone) Surfaces

- (a) 1<sup>st</sup> coat: Titanium Masonry Primer.
- (b) 2<sup>nd</sup> and 3<sup>rd</sup> coat: Titanium Paints Quality Products.

<b><u>Application Method:</u></b>	Brush, roller or airless spray.
<b><u>Spreading Rate:</u></b>	± 7.5m <sup>2</sup> per litre per coat on very smooth surfaces.
<b><u>Cleaning of Utensils:</u></b>	Mineral Turpentine.
<b><u>Packaging Sizes:</u></b>	20 L, 5 L and 1 L
<b><u>Colour Range:</u></b>	White