

PRODUCT DATA

UNIVERSAL UNDERCOAT



Type

An Alkyd Resin-based Intermediate Coat.

Appearance

Dries to a tough film with a very slight sheen.

Properties and Uses

Titanium Universal Undercoat is suitable for use both internally and externally on suitably primed and prepared surfaces.

Surface Preparation

Essential for good paint performance is a sound substrate that has been properly cleaned and prepared. On existing painted surfaces it is recommended that a small section of paint be removed to establish the condition of the original paint and the substrate. Where there is doubt, the paint must be removed to a sound base. All surfaces must be dry, free from loose and flaky material, grease and fungus prior to applying the new paint system.

Application Instructions

These instructions are issued as an aid in determining correct surface preparation, mixing and application procedure and should be closely followed to obtain maximum service from the material.

- (a) Titanium Universal Undercoat may be used over suitably primed metal and wood surfaces.
- (b) If used over existing gloss finishes, the surface should first be sanded well before application of the Universal Undercoat to ensure that adequate key is obtained.
- (c) A minimum of 16 hours drying time should be allowed before over-coating.

<u>Application Method:</u>	Brush, mohair roller or airless spray.
<u>Spreading Rate:</u>	± 8.5m ² per litre.
<u>Drying Time:</u>	Surface dry 4 hours and hard dry 16 hours at 25°C.
<u>Cleaning of Utensils:</u>	Mineral Turpentine.
<u>Packaging Sizes:</u>	5 L and 1 L
<u>Colour Range:</u>	White only.